

Supporting Information

Table 1. *R/S* Copolymerization of **1**.

ee (%)	Yield (%) ^{a)}	M_n ^{b)}	M_w/M_n ^{b)}	$[\alpha]_D$ (deg) ^{c)}
90	79	13000	3.45	+1850
70	77	25000	2.52	+1920
50	80	24000	3.38	+1890
30	82	33000	3.77	+1840
20	91	23000	1.62	+1560
10	86	46000	3.47	+899

^{a)} *n*-hexane-insoluble part. ^{b)} Estimated by GPC (CHCl₃, PSt standards). ^{c)} $c =$

0.11–0.079 (g/dL) in CHCl₃.